



**EXT. REFLECTIVE BLUE 20**

External Reflective Blue 20 highly effective at reducing solar heat gain, whilst at the same time continuing to allow some natural light transmission. They provide effective protection against solar glare, conveying a touch of colour and originality to the external aspect of a building.



Tintfit Window Films warranty  
**VERTICAL 3 YEARS**  
**HORIZONTAL N/A**



Fire-resistance rating  
**M1**



Storage from -5°C to +40°C  
**3 YEARS**



REACH RoHS compliant  
**RESPECTED**

**TECHNICAL DATASHEET**


Data calculated based on film applied to clear glass 3 mm thick (\*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	15 %
Reflection of external visible light	18 %
Reflection of internal visible light	62 %
Total solar energy rejected	79 %
Total solar energy rejected 2	84 %
Solar ratio :	
Solar energy reflection	35 %
Solar energy absorption	55 %
Solar energy transmission	10 %
Reduction in Solar Glare	84 %
g-value	0.24
u-value	5.13
Shading coefficient	0.2
Installation type : External application	
Roll length	30,5 m
PET / PVC composition	PET
Thickness	50 µ

Colour : BLUE

**CONSTRUCTION**

1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
2. Dyed polyester without optical distortion
3. Bonding adhesive
4. High optical quality polyester, with anti IR metal particles deposit
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation



**MAINTENANCE INSTRUCTIONS**

Soapy water solution, do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

*Non-contractual data, Tintfit Window Films reserves the right to modify the composition of its films at any time.*

**INSTALLATION ADVICE**

Vertical installation and on standard glass surface\*

Clear single pane	✓
Tinted single pane	!
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	!
Reflective tinted double pane	✓
Gas-filled double pane - Low E	!
STADIP EXT. clear double pane	✗
STADIP INT. clear double pane	!

✓ Yes    ! Caution    ✗ No

\*Recommendations provided on the basis of a glazed surface covering up to 2.5m<sup>2</sup>, contact us for definitive details or to obtain a thermal chock analysis report.