



NON REF. BOTTLE GREEN 40

Applied to clear glass, the Non Reflective Bottle Green 40 film bestows a green tint to the glass without diminishing its transparent properties. It is the perfect way to enliven any interior glazing (such as partitions, shower screens, etc.) with a touch of colour.



Tintfit Window Films warranty

5 YEARS



Storage from -5°C to +40°C

3 YEARS



REACH RoHS compliant

RESPECTED

TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	40 %
Reflection of external visible light	9 %
Reflection of internal visible light	9 %
Total solar energy rejected	30 %
Total solar energy rejected 2	24 %
Solar ratio :	
Solar energy reflection	10 %
Solar energy absorption	45 %
Solar energy transmission	45 %
Reduction in Solar Glare	60 %
g-value	0.7
u-value	5.7
Shading coefficient	
Installation type : Internal application	
Roll length	30,5 m
PET / PVC composition	PET
Thickness	40 µ

Colour : GREEN

CONSTRUCTION

1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
2. Dyed polyester without optical distortion
3. Bonding adhesive
4. High optical quality polyester
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation



MAINTENANCE INSTRUCTIONS

Soapy water solution, do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data, Tintfit Window Films reserves the right to modify the composition of its films at any time.

INSTALLATION ADVICE

Vertical installation and on standard glass surface*

Clear single pane	✓
Tinted single pane	!
Reflective tinted single pane	✓
Clear double pane	!
Tinted double pane	✗
Reflective tinted double pane	✓
Gas-filled double pane - Low E	!
STADIP EXT. clear double pane	!
STADIP INT. clear double pane	✗

✓ Yes ! Caution ✗ No

*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.