



PREM PLUS MEDIUM 25

With its well-appointed metallised design, the Premium Plus Medium 25 automotive film combines discretion and privacy from prying eyes with technical efficiency in reflecting solar heat.



Tintfit Window Films warranty
5 YEARS



Storage from -5°C to +40°C
3 YEARS



REACH RoHS compliant
RESPECTED

TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	20 %
Reflection of external visible light	7 %
Reflection of internal visible light	5 %
Total solar energy rejected	53 %
Total solar energy rejected 2	49 %
Solar ratio :	
Solar energy reflection	10 %
Solar energy absorption	70 %
Solar energy transmission	20 %
Reduction in Solar Glare	79 %
g-value	-
u-value	-
Shading coefficient	
Installation type : Internal application	
Roll length	30,5 m
PET / PVC composition	PET
Thickness	55 µ

Colour : BLACK

CONSTRUCTION

1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
2. Dyed polyester without optical distortion, with anti IR metal particles deposit
3. Bonding adhesive
4. Dyed polyester without optical distortion
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation



MAINTENANCE INSTRUCTIONS

Soapy water solution, do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data, Tintfit Window Films reserves the right to modify the composition of its films at any time.

INSTALLATION ADVICE

Vertical installation and on standard glass surface*

Clear single pane	✓
Tinted single pane	✗
Reflective tinted single pane	✓
Clear double pane	✗
Tinted double pane	✗
Reflective tinted double pane	✓
Gas-filled double pane - Low E	✗
STADIP EXT. clear double pane	✗
STADIP INT. clear double pane	✗

✓ Yes ! Caution ✗ No

*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.